



The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E).,Songjiang
Shanghai China
Postal Code: 201613
Tel:(021)57747878
Fax:(021)51685279
Website: <https://www.escort.com.cn/CN>

TEST REPORT

MATERIAL : HNBR 80 DURO BLACK

COMPOUND NO: H8001B

Physical Properties (Press Cure:170°CX10min Post Cure:175°CX4h)	Requirement	Test result
Hardness,Point 硬度(邵A)	75.00~85.00	79.00
Tensile Strength,min,Mpa 拉力強度	20.00	20.20
Ultimate Elongation,min,% 延伸率	150.00	192.00
Specific Gravity, 比重		1.30

Heat Resistance 70h@150°C 老化試驗

Change in hardness,max,Point 硬度變化(邵A)	+10.00	+3.00
Change in tensile strength,max,% 拉伸強度變化率	-15.00	-2.00
Change in ultimate elongation,max,% 扯斷伸長率變化率	-25.00	-21.00

Compression Set 22h@150°C 壓縮永久變形試驗

Compression set,Method B,max,% 壓縮永久變形	10.00
---------------------------------------	-------

Fluid Resistance No.1 Oil Resistance 70h@150°C 1號油試驗

Change in hardness,Point 硬度變化	-5.00~10.00	+0.00
Change in tensile strength,max,% 拉力強度變化率	-20.00	+9.00
Change in ultimate elongation,max,% 延伸率變化率	-30.00	-9.00
Change in volume,% 體積變化率	-10.00~5.00	-1.00

Fluid Resistance No.3 Oil Resistance 70h@150°C 3號油試驗

Change in hardness,Point 硬度變化	-15.00	-8.00
Change in tensile strength,max,% 拉力強度變化率	-40.00	-7.00
Change in ultimate elongation,max,% 延伸率變化率	-30.00	-2.00
Change in volume,% 體積變化率	+25.00	+12.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
THIS COMPOUND H8001B CAN MEET ASTM 2000 M4DH820A26B16EQ16EO36

