

TEST REPORT

MATERIAL : HNBR 90 DURO BLACK

COMPOUND NO: H9001B

Physical Properties (Press Cure:170°CX10min Post Cure:175°CX4h)	Requirement	Test result
Hardness, Point 邵A	85.00~95.00	90.00
Tensile Strength, min, Mpa 拉力強度	20.00	22.50
Ultimate Elongation, min, % 延伸率	100.00	112.00
Specific Gravity, 比重		1.28

Heat Resistance 70h@150°C 老化試驗

Change in hardness, max, Point 邵A	+10.00	+0.00
Change in tensile strength, max, % 拉伸強度變化率	-25.00	+10.00
Change in ultimate elongation, max, % 扯斷伸長率變化率	-30.00	-4.00

Compression Set 22h@150°C 壓縮永久變形試驗

Compression set, Method B, max, % 壓縮永久變形	50.00	6.00
--	-------	------

Fluid Resistance No.1 Oil Resistance 70h@150°C 1號油試驗

Change in hardness, Point 邵A	-5.00~10.00	-1.00
Change in tensile strength, max, % 拉力強度變化率	-20.00	+4.00
Change in ultimate elongation, max, % 延伸率變化率	-30.00	-4.00
Change in volume, % 體積變化率	±5.00	-2.00

Fluid Resistance No.3 Oil Resistance 70h@150°C 3號油試驗

Change in hardness, Point 邵A	-15.00	-10.00
Change in tensile strength, max, % 拉力強度變化率	-30.00	-7.00
Change in ultimate elongation, max, % 延伸率變化率	-30.00	+1.00
Change in volume, % 體積變化率	+25.00	+10.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
THIS COMPOUND H9001B CAN MEET ASTM 2000 M3DH920A26B16EQ16EO36

