

TEST REPORT

MATERIAL : NBR 90 DURO RED

COMPOUND NO: N9001R

Physical Properties (Press Cure:170°CX10min Post Cure:150°CX1h)	Requirement	Test result
Hardness, Point 邵A	85.00~95.00	92.00
Tensile Strength, min, Mpa 拉力強度	7.00	10.70
Ultimate Elongation, min, % 延伸率	100.00	161.00
Specific Gravity, 比重		1.55

Heat Resistance 70h@100°C 老化試驗

Change in hardness, max, Point 邵A	+15.00	-2.00
Change in tensile strength, max, % 拉伸強度變化率	-20.00	+2.00
Change in ultimate elongation, max, % 扯斷伸長率變化率	-40.00	+4.00

Compression Set 22h@100°C 壓縮永久變形試驗

Compression set, Method B, max, % 壓縮永久變形	25.00	19.00
--	-------	-------

Fluid Resistance No.1 Oil Resistance 70h@100°C 1號油試驗

Change in hardness, Point 邵A	-5.00~15.00	-2.00
Change in tensile strength, max, % 拉力強度變化率	-25.00	+8.00
Change in ultimate elongation, max, % 延伸率變化率	-45.00	+2.00
Change in volume, % 體積變化率	-10.00~5.00	-1.00

Fluid Resistance No.3 Oil Resistance 70h@100°C 3號油試驗

Change in hardness, Point 邵A	-20.00~0.00	-13.00
Change in tensile strength, max, % 拉力強度變化率	-45.00	-5.00
Change in ultimate elongation, max, % 延伸率變化率	-45.00	+4.00
Change in volume, % 體積變化率	0.00~35.00	+13.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
THIS COMPOUND N9001R CAN MEET ASTM 2000 M6BG907A14B14EQ14EO34

