



The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd  
NO.205 Jiangnan RD(E), Songjiang  
Shanghai China  
Postal Code: 201613  
Tel: (021) 57747878  
Fax: (021) 51685279  
Website: <https://www.escort.com.cn/CN>

## TEST REPORT

MATERIAL: SIL 80 DURO CLEAR

COMPOUND NO: S8001C

| Physical Properties (Press Cure:170°CX10min Post Cure:200°CX4h) | Requirement | Test result |
|-----------------------------------------------------------------|-------------|-------------|
| Hardness, Point 硬度(邵A)                                          | 75.00~85.00 | 83.00       |
| Tensile Strength, min, Mpa 拉力強度                                 | 6.00        | 7.00        |
| Ultimate Elongation, min, % 延伸率                                 | 100.00      | 132.00      |
| Specific Gravity, 比重                                            |             | 1.21        |

### Heat Resistance 70h@225°C 老化試驗

|                                                |        |        |
|------------------------------------------------|--------|--------|
| Change in hardness, max, Point 硬度變化(邵A)        | +10.00 | +0.00  |
| Change in tensile strength, max, % 拉伸強度變化率     | -25.00 | -14.00 |
| Change in ultimate elongation, max, % 扯斷伸長率變化率 | -30.00 | -13.00 |

### Compression Set 22h@175°C 壓縮永久變形試驗

|                                          |       |       |
|------------------------------------------|-------|-------|
| Compression set, Method B, max, % 壓縮永久變形 | 25.00 | 14.00 |
|------------------------------------------|-------|-------|

### Fluid Resistance No.1 Oil Resistance 70h@150°C 1號油試驗

|                                              |             |       |
|----------------------------------------------|-------------|-------|
| Change in hardness, Point 硬度變化               | -15.00~0.00 | -8.00 |
| Change in tensile strength, max, % 拉力強度變化率   | -20.00      | +3.00 |
| Change in ultimate elongation, max, % 延伸率變化率 | -20.00      | +3.00 |
| Change in volume, % 體積變化率                    | 0.00~10.00  | +7.00 |

### Fluid Resistance No.3 Oil Resistance 70h@150°C 3號油試驗

|                                            |        |        |
|--------------------------------------------|--------|--------|
| Change in hardness, Point 硬度變化             | -30.00 | -23.00 |
| Change in tensile strength, max, % 拉力強度變化率 | +60.00 | +39.00 |

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY  
THIS COMPOUND S8001C CAN MEET ASTM 2000 M5GE806A19B37EO16EO36

