



The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E).,Songjiang
Shanghai China
Postal Code: 201613
Tel:(021)57747878
Fax:(021)51685279
Website: <https://www.escort.com.cn/CN>

TEST REPORT

MATERIAL : CR 60 DURO BLACK

COMPOUND NO: C6001B

Physical Properties (Press Cure:170°CX10min Post Cure:100°CX1h)	Requirement	Test result
Hardness,Point 硬度(邵A)	55.00~65.00	65.00
Tensile Strength,min,Mpa 拉力強度	10.00	13.50
Ultimate Elongation,min,% 延伸率	350.00	354.00
Specific Gravity, 比重		1.47
Heat Resistance 70h@100°C 老化試驗		
Change in hardness,max,Point 硬度變化(邵A)	+15.00	+2.00
Change in tensile strength,max,% 拉伸強度變化率	-15.00	-5.00
Change in ultimate elongation,max,% 扯斷伸長率變化率	-40.00	-15.00
Compression Set 22h@100°C 壓縮永久變形試驗		
Compression set,Method B,max,% 壓縮永久變形	35.00	31.00
Fluid Resistance No.1 Oil Resistance 70h@100°C 1號油試驗		
Change in hardness,Point 硬度變化	±10.00	-1.00
Change in tensile strength,max,% 拉力強度變化率	-30.00	+4.00
Change in ultimate elongation,max,% 延伸率變化率	-30.00	-12.00
Change in volume,% 體積變化率	-10.00~15.00	-4.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
THIS COMPOUND C6001B CAN MEET ASTM 2000 M3BC610A14B14EQ14

