



The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E).,Songjiang
Shanghai China
Postal Code: 201613
Tel:(021)57747878
Fax:(021)51685279
Website: <https://www.escort.com.cn/CN>

TEST REPORT

MATERIAL : EP 70 DURO PRO CURED RED

COMPOUND NO: E7021R

Physical Properties (Press Cure:170°CX10min Post Cure:150°CX1h)	Requirement	Test result
Hardness,Point 硬度(邵A)	65.00~75.00	71.00
Tensile Strength,min,Mpa 拉力強度	7.00	7.30
Ultimate Elongation,min,% 延伸率	200.00	324.00
Specific Gravity, 比重		1.21
Heat Resistance 70h@125°C 老化試驗		
Change in hardness,max,Point 硬度變化(邵A)	+10.00	+4.00
Change in tensile strength,max,% 拉伸強度變化率	-20.00	+22.00
Change in ultimate elongation,max,% 扯斷伸長率變化率	-40.00	-13.00
Compression Set 22h@125°C 壓縮永久變形試驗		
Compression set,Method B,max,% 壓縮永久變形	70.00	12.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
THIS COMPOUND E7021R CAN MEET ASTM 2000 M3CA707A25B35

