

TEST REPORT

MATERIAL : ACM 80 DURO BLACK

COMPOUND NO: A8001B

Physical Properties (Press Cure:170°CX10min Post Cure:175°CX3h)	Requirement	Test result
Hardness,Point 硬度(邵A)	75.00~85.00	83.00
Tensile Strength,min,Mpa 拉力強度	7.00	11.50
Ultimate Elongation,min,% 延伸率	100.00	138.00
Specific Gravity, 比重		1.34

Heat Resistance 70h@175°C 老化試驗

Change in hardness,max,Point 硬度變化(邵A)	+10.00	+2.00
Change in tensile strength,max,% 拉伸強度變化率	-30.00	-8.00
Change in ultimate elongation,max,% 扯斷伸長率變化率	-40.00	-10.00

Compression Set 22h@175°C 壓縮永久變形試驗

Compression set,Method B,max,% 壓縮永久變形	60.00	27.00
---------------------------------------	-------	-------

Fluid Resistance No.1 Oil Resistance 70h@150°C 1號油試驗

Change in hardness,Point 硬度變化	±5.00	+1.00
Change in tensile strength,max,% 拉力強度變化率	-20.00	+16.00
Change in ultimate elongation,max,% 延伸率變化率	-30.00	-2.00
Change in volume,% 體積變化率	±5.00	-1.00

Fluid Resistance No.3 Oil Resistance 70h@150°C 3號油試驗

Change in hardness,Point 硬度變化	-20.00	-9.00
Change in tensile strength,max,% 拉力強度變化率	-40.00	+7.00
Change in ultimate elongation,max,% 延伸率變化率	-30.00	-12.00
Change in volume,% 體積變化率	+25.00	+11.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
THIS COMPOUND A8001B CAN MEET ASTM 2000 M3EH807A27B17EQ16EO36

